



RC3 CLEAR THIN SPREAD ADHESIVE

Divergent Clear RC3 CTS Adhesive is a solvent free, non-flammable, freeze-thaw stable adhesive specifically designed for the installation of Vinyl Composition Tile. This adhesive has high shear strength, fast dry times with low VOC's and aggressive tack when it dries. It dries clear so your lay out lines are visible through the adhesive.

Packaging: 4 gallon pail



Key Features

- › High solids
- › Solvent free
- › Extended working time of up to 16 hours
- › Moisture resistant up to 95% RH and 10 lbs. MVER
- › Dries fast
- › Moisture resistant



OUR EXPERIENCE ENSURES YOUR SUCCESS

1-877-458-3833 · 1-877-GLU-DUDE · sonny@divergentadhesives.com · divergentadhesives.com

©2022 Divergent Adhesives, LLC.



RC3 CLEAR THIN SPREAD ADHESIVE

COVERAGE

Flooring	Trowel Recommendation	Approximate Spread Rate
Vinyl Composition Tile Porous and non-porous	1/16" x 1/32" x 1/32"	200-225 ft ² / Gallon*

*Spread rate will vary based on substrate texture and absorption rate, trowel angle and other factors. Use this chart as a reference only.

APPROVED SUBSTRATES

- › Concrete
- › APA rated plywood
- › Portland based underlayment
- › Terrazzo
- › Properly prepared gypcrete / lightweight concrete
- › Radiant heated floors
- › Single layer of approved, fully adhered resilient flooring

SUBSTRATE PREPARATION

All substrates should be prepared in accordance with flooring manufacturers guidelines and/or ASTM F710. Moisture tests are required on all concrete subfloors regardless of age or elevation. Moisture testing must be performed in accordance with the most current ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride, with levels not to exceed 10 lbs. per 24 hours per 1000 sf and ASTM F2170 Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes with readings not exceeding 95%. The pH must be between 7-10.

STORAGE

Protect adhesive from freezing. Store material in temperature-controlled buildings.

SHELF LIFE

Unopened packaging stored in proper conditions have a shelf life of 2 years.

WARRANTY

Divergent Adhesives LLC. Offers a limited liability warranty for this material when used in accordance with the label and TDS.

TECHNICAL DATA

Base Polymer	Acrylic
Color	Tan
Shelf Life	2 years in unopened container
Application Temp. Range	60°-95° F
Dry Time	Dries to no transfer in 30 minutes*
Open Time	Up to 16 hours**
VOC Content	0 grams / Liter

*Ambient temperature and humidity will greatly affect the dry time of the adhesive.

**Keep the adhesive clean and free from debris during installation.

INSTALLATION INSTRUCTIONS

All subfloor preparation instructions from the flooring manufacturer and current industry standards must be followed. Moisture testing is required on all concrete subfloors, regardless of grade level or if the concrete is freshly poured or is classified as an older slab. All moisture testing should be performed using the most up to date ASTM F1869 Anhydrous Calcium Chloride and ASTM F2170.

Spread the adhesive using the recommended trowel from the chart above. The adhesive will turn from tan to clear when it is ready to receive flooring. Once there is no transfer, and the adhesive is clear, you can safely apply flooring for up to 16 hours. Ambient temperature and humidity will greatly affect the dry time of the adhesive. It is the responsibility of the installer to note when the adhesive is ready to receive flooring. Once the flooring has been installed, it must be rolled using a 100 lb. 3-section roller, in both directions.

For Technical Support contact your local Divergent Adhesives Sales Manager or call 407-383-6446.

RESTRICTIONS

1. Refer to flooring manufacturer for recommendation.
2. For interior installations only.
3. Do not install when MVER is over 10 lbs. per 1,000 sf per 24 hours per ASTM F1869.
4. Do not install when Relative Humidity is over 95% when tested in accordance with ASTM F2170.
5. It is the sole responsibility of the installer to determine the suitability and compatibility of the adhesive for the intended application.

CLEAN UP

Fresh adhesive can be cleaned up using water and a clean cloth, dried adhesive will require the use of mineral spirits or other clear solvent.



OUR EXPERIENCE ENSURES YOUR SUCCESS

1-877-458-3833 · 1-877-GLU-DUDE · sonny@divergentadhesives.com · divergentadhesives.com

©2022 Divergent Adhesives, LLC.